

---

# CyGuard-prime

**Product Descriptions:** -A two pack epoxy polyamide anticorrosive primer with excellent anticorrosive properties.

---

**Intended Uses:** - Can be used for structural steel where high degree of corrosion resistance is required. Ideal for saline environment. Imparts good Adhesion on well prepared Aluminium & Galvanised steel surface.

---

<b>Product Information:</b> -Colours	Buff,Grey,Black,,Redoxide.
Finish/Sheen	Egg shell.
Volume Solids	56% (May Vary as per colour)
Mix Ratio	4:1 / Base: Hardner
Typical Film Thickness	35-100 microns dry
Theoretical Coverage	11.20 (m <sup>2</sup> /lt) at 40 microns dft, allow appropriate loss factors
Method of Application	Spray, Brush, Roller
Induction Period	None required

---

**Dying Information:** - 30°C

**Touch dry:** - 10 minute

**Tack Free:** - 2 Hours

**Hard Dry:** - Over night

**Pot Life:** - 4 - 6 Hrs

### Direction for use

1. Ensure the surface to be painted is free from any loose paint, dust or grease
2. Stir well the paint thoroughly in the container.
3. Adjust the viscosity 20-22 Sec. Mix the thinner & hardner with paint as per recommended ratio ( by volume) for spraying.
4. Stain the paint with bloating nylon no. 12.
5. Apply two coats of the paint on the surface.
6. Keep the pressure to 2.8 - 3.5 kg / sq. cm. & air should be completely dry and free from moisture.

---

**Warning: -** Flammable liquid and vapor

**Cause: -** Eye irritation  
May cause skin irritation

---

### First aid:-

**1. For Eyes: -** 1. Immediately flush with plenty water  
2. Get medical attention  
3. Remove affected cloths

**2. On Skin: -** 1. Immediately flush with plenty of water  
2. Remove contaminated clothing.  
3. Wash clothing before using.

---



## CyGuard-Prime Epoxy primer

---

**Handling: -** Keep away from heat, sparks and flame.  
Avoid contact with eyes, skin and clothing.

---

**Storage: -** Keep in a cool, dry and ventilated place.  
Stable under normal condition.

---

**Precautions: -** Do not add any thinner or material in paint, which is not recommended.